



TECHNICAL DATA SHEET

Ref.: Technische Fiches\TDS ALUSPRAY.EN

ZM-RE-PRO-04-B (02/09/14)

Product code: 308/ZASP

p. 1/4

www.zinga.eu

8/12/21 - v2.0

ALUSPRAY

ALUSPRAY is an aerosol coating based on aluminium flakes. It can be applied either without primer on an old, non-corroded hot-dip galvanisation or metallisation layer or as topcoat on top of ZINGA. ALUSPRAY is mainly applied for esthetical reasons as it gives a nice aluminium aspect.

PHYSICAL DATA AND TECHNICAL INFORMATION

WET PRODUCT

Components	- Aluminium powder - Aromatic hydrocarbons - Binder
Density	0,656 Kg/dm ³ (± 0,05 Kg/dm ³) at 20°C
Propellant	Dimethylether
Content	Liquid
Flashpoint	-41°C (~ propellant)
VOC	619 g/L

DRY FILM

Colour	Aluminium (~RAL 9006: comparable to hot-dip)
Special features	- Good resistance to mechanical shocks, abrasion and erosion - Very economical - Efficient and solid
Temperature resistance dry film	- Minimum -40°C - Maximum +150°C

PACKING

500 mL	Spray can
--------	-----------

CONSERVATION

Shelf life	5 years in original, unopened packing and shaken mechanically after 3 years.
Storage	Store vertically in a dry place with a temperature between 5°C and 35°C (preferably at room temperature ±18°C)

CONDITIONS

SURFACE PREPARATION

Surface preparation	<ul style="list-style-type: none"> - ALUSPRAY can be applied on ferro-metals and (damaged) zinc surfaces. - For optimal performance, the metal should first be degreased, preferably by steam-cleaning. Alternatively, the surface can be degreased using solvent (e.g. ZINGASOLV), but never use white spirit. - For optimal performance, clean to SA 2,5 (ISO 8501:2007). For non-critical (small) areas, cleaning to St 3 is sufficient (using a steel brush).
Roughness	<ul style="list-style-type: none"> - ALUSPRAY should be applied on a metal substrate that has a roughness grade of fine to medium G (Rz 50 to 100 µm) according to the standard ISO 8503-2:2012. - Such a level of roughness is not needed when ZINGA is applied on a hot-dip galvanisation or a metallisation layer, or when it is applied on top of an existing ZINGA. Old hot-dipped surfaces have adequate roughness, new hotdipped surfaces require a sweep blast - For small, non-critical areas, roughness can be obtained by using a steel wire brush or sand paper.
Maximum time to application	Apply the ALUSPRAY as soon as possible on the prepared metal substrate before any contamination or corrosion occurs before coating. Otherwise the surface must be cleaned again as described above.

ENVIRONMENTAL CONDITIONS DURING APPLICATION

Ambient temperature	<ul style="list-style-type: none"> - Minimum 5°C - Maximum 40°C
Relative humidity	<ul style="list-style-type: none"> - Maximum 90% - Do not apply on a damp or wet surface
Surface temperature	<ul style="list-style-type: none"> - Minimum 3°C above the dew point. - No visual presence of water or ice - Maximum 60°C

APPLICATION INSTRUCTIONS

GENERAL

Shaking	ALUSPRAY must be shaken thoroughly before application. Shake the can vigorously for minimum 30 seconds after liberating the balls. Repeat this every time the can is not used for some time.
Application	Keep the spray between 10 and 20 cm away from the substrate and move in a continuous speed from left to right. Repeat with a spray application from top to bottom.
Cleaning	Cleaning of equipment or spills with ZINGASOLV.

OTHER INFORMATION

COVERAGE AND CONSUMPTION

Theoretical coverage	For 40 µm DFT: 4,0 m ² /L
Practical coverage and consumption	Depends upon the roughness profile of the substrate and the application method

DRYING PROCESS AND OVERCOATING

Drying process	ALUSPRAY dries by evaporation of the solvent. The drying process is influenced by the total WFT, the ambient air (humidity and temperature) and the steel surface temperatures.
Drying time	For 40 µm DFT at 20°C in a well-ventilated environment: » Dust dry: 15-30 minutes » Touch dry: 30-45 minutes » Dry to handle: 1,5 hours » Fully cured: 24 hours
Overcoating with a new layer of ALUSPRAY	- It is advised to wait until the ALUSPRAY is at least touch dry before applying a second layer - Make sure the ALUSPRAY layer is clean before overcoating

RECOMMENDED SYSTEM

Unique system	ALUSPRAY is advised for touch-up (HDG, metallisation or on ZINGA) and application on small areas only. It should be applied in two layers.
---------------	--

For more specific and detailed recommendations concerning the application of ALUSPRAY, please contact the Zingametall representative.

For detailed information about the health and safety hazards and precautions for use, refer to the ALUSPRAY safety data sheet.

